

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 160 284 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

05.12.2001 Bulletin 2001/49

(51) Int Cl.7: **C08L 27/12, B32B 27/30**

(21) Application number: **01112037.5**

(22) Date of filing: **23.05.2001**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: **01.06.2000 JP 2000164293**

(71) Applicant: **MATSUSHITA ELECTRIC INDUSTRIAL
CO., LTD.**

Kadoma-shi, Osaka 571-8501 (JP)

(72) Inventors:

- **Kiyomura, Yoshihiro**
Oonjo-shi, Fukuoka 816-0941 (JP)
- **Kama, Hirofumi**
Oomuta-shi, Fukuoka 836-0006 (JP)
- **Noda, Hiroyuki**
Ogoori-shi, Fukuoka 838-0107 (JP)

(74) Representative: **Balsters, Robert et al**
Novapat International SA,
9, rue du Valais
1202 Genève (CH)

(54) **Fluorine rubber composition, fixing member, fixing device, fixing method, and method of manufacturing fixing device**

(57) A fluorine rubber composition used for the surface layer material of a fixing member to fix a toner transferred onto a recording material comprises fluorine rubber having a polymerization degree based on vinylidene fluoride. The fixing member includes a base material, and a surface layer material disposed on the surface of the base material, and the surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride. Preferably, the fluorine rubber

composition contains a reinforcing agent, antacid, vulcanizing agent, vulcanization accelerator, spherical filler, and solvent. Preferably, the fixing member has numerous fine convex portions on its surface. Accordingly, the amount of the toner adhering to the surface of the fixing member is reduced. Thus, generation of offset trouble can be reliably prevented for a long period of time. As a result, the durability of the fixing member will be improved.

EP 1 160 284 A2

Description**Field of the Invention**

5 [0001] The present invention relates to a fluorine rubber composition used in an image picture forming apparatus, a fixing member, a fixing device, a fixing method, and a method of manufacturing the fixing device.

Background of the Invention

10 [0002] In an image picture forming apparatus, a toner transferred onto a recording material such as paper or the like is fixed by a fixing device installed in the apparatus.

[0003] Fig. 6 is a sectional view of a conventional fixing device. The fixing device which serves to fix a toner 13 transferred onto a recording material 12 comprises a fixing roller 201 being a fixing member, a press roller 102 opposing to the fixing roller 201, and a web 104 impregnated with silicone oil as a lubricant to prevent sticking of toner T to surface layer 203 of the fixing roller 201. The fixing roller 201 and the press roller 102 are formed by coating a core bar 105 with an elastic body 106. A heater 107 as a heat source is disposed in the core bar 105 of the fixing roller 201.

[0004] Recording material 12 such as paper or the like with a picture image formed thereon by transferring the toner 13 is caught between the fixing roller 201 and the press roller 102, and is heated and pressed, then the toner 13 is fixed on the recording material 12.

20 [0005] However, the toner 13 increases in viscosity due to the heat. Accordingly, as shown in the partly enlarged view of Fig. 3 showing a state of picture image fixation in a conventional fixing device, a part of the toner 13 on the recording material 12 adheres to the surface of the fixing roller 201. As a result, when the next recording material 12 advances toward the fixing roller 201 heated, the toner 13, increasing in viscosity and adhering to the fixing roller 201, is partially transferred onto the next recording material 12. This process is generally called offset, and frequent generation of offset means the termination of the life of the fixing device.

25 [0006] In order to prevent generation of such offset, in the prior art, the toner is fixed by heat and pressure of the fixing roller 201 and the press roller 102 while applying a lubricant such as silicone oil to the fixing roller 201. There are some different methods of lubricant application to the fixing roller 201. For examples, as shown in Fig. 6, a lubricant is applied to the fixing roller 201 by contacting the web 104 with the fixing roller 201. The web 104 is pressed against the fixing roller 201 by a web pressing roller 108 and is taken up onto a web take-up roller 110 from a web feed roller 109 at a predetermined speed.

30 [0007] However, in a conventional fixing device, the surface layer 203 of the fixing roller 201 is formed of silicone rubber, fluorine rubber or the like. Since the fixing roller 201 is heated, the surface layer 203 of the fixing roller 201 is deteriorated due to the heat. Further, in use of the fixing roller 201 for a long period of time, the surface layer 203 becomes worn and scratched due to sticking of paper and dust. In case the surface layer 203 is worn or scratched, the toner 13 will stick to the surface layer 203 of the fixing roller 201 despite that the surface layer 203 is coated with a lubricant. That is, there are not a few chances of generation of offset even when the surface layer 203 is coated with a lubricant.

35 [0008] A fixing device capable of preventing such offset is disclosed in Japanese Laid-Open Patent No. 4-319980. The fixing device disclosed in Japanese Laid-Open Patent No. 4-319980 comprises a fixing roller and a roller polishing means to polish the fixing roller surface. The fixing roller used is a single-layer roller formed of methyl or methylvinyl type silicone rubber, and the silicone oil used is methylphenyl type silicone oil.

40 [0009] In such fixing roller, the fixing roller surface is always refreshed since the fixing roller surface is polished by the roller polishing means. As a result, generation of offset can be prevented. Also, since a single-layer roller formed of silicone rubber is employed, polishing the fixing roller surface does not cause the under layer material to be exposed, thereby improving the durability.

45 [0010] However, in such prior art fixing device, the optimum conditions for roller polishing vary with various factors such as grain sizes of polishing material, grain shapes, its contents in silicone oil, abutment pressures to the fixing roller of cleaning web as a roller polishing means, abutment areas, fiber density of web, and material quality of roller rubbers. Accordingly, it is difficult to find and maintain optimum values in relation to a number of these factors. Further, as the fixing roller surface is polished, the roller will be reduced in diameter through use for a long period of time. Consequently, the above-mentioned factors at their optimum values are influenced, gradually going wrong.

50 [0011] The present invention is intended to improve the durability of the fixing member, preventing generation of offset reliably for a long period of time by lessening the amount of toner sticking to the fixing member surface without polishing the fixing member surface of a roller or the like.

Summary of the Invention

[0012] A fluorine rubber composition of the present invention, used for the surface layer material of a fixing member to fix a toner transferred onto a recording material, comprises:

- (a) fluorine rubber having a polymerization degree based on vinylidene fluoride; and
- (b) at least one selected from the group consisting of a reinforcing agent, an antacid, a vulcanizing agent, a vulcanization accelerator, a spherical filler, and an organic solvent.

[0013] A fixing member of the present invention for fixing a toner transferred onto a recording material comprises:

- a base material and
- a surface layer material disposed on the base material,
- wherein the surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride.

[0014] A fixing device of the present invention for fixing a toner transferred onto the surface of a recording material comprises:

- a fixing roller;
- a press roller disposed opposing the fixing roller; and
- a web to apply a lubricant to the surface of the fixing roller,
- wherein the fixing roller comprises a base material and a surface layer material disposed on the surface of the base material;
- the surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride; and
- a recording material having the toner transferred thereon passes between the fixing roller and the press roller while being pressed by the fixing roller and the press roller so that the surface layer material comes in contact with the toner, and thereby, the toner is fixed on the recording material.

[0015] A fixing method of the present invention comprises:

- (a) a step of transferring a toner onto the surface of a recording material;
- (b) a step of passing the recording material, having the toner transferred thereon, between a fixing roller and a press roller, under pressures applied by the fixing roller and the press roller,
- wherein the fixing roller comprises a base material and a surface layer material disposed on the surface of the base material;
- the recording material passes between the rollers in a manner such that the toner is positioned at the fixing roller side;
- the surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride; and
- (c) a step of fixing the toner, pressed by the fixing roller and the press roller, on the surface of the recording material.

[0016] A method of manufacturing a fixing device of the present invention for fixing a toner transferred onto the surface of a recording material comprises the steps of:

- (a) manufacturing a fixing roller; and
- (b) manufacturing a press roller,

wherein the step of manufacturing the fixing roller comprises the steps of:

- (1) manufacturing a paint;
- wherein the step of manufacturing the paint includes a step of mixing and dispersing fluorine rubber having a polymerization degree based on vinylidene fluoride, a vulcanizing agent, and a solvent;
- (2) applying the paint onto the surface of a base material having a spherical shape; and
- (3) drying and hardening the paint applied to the surface of the base material to form a surface layer material.

[0017] Preferably, the fluorine rubber contains at least one copolymer selected from the group consisting of a copolymer of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene; a copolymer of tetrafluoroethylene, vinylidene

fluoride and propylene; and a copolymer of vinylidene fluoride and hexafluoropropylene.

[0018] By the above configuration, the amount of toner sticking to the surface of a fixing member is reduced. Accordingly, generation of offset can be reliably prevented for a long period of time. Further, the durability of the fixing member will be improved.

Brief Description of the Drawings

[0019]

Fig. 1 is a sectional view of a fixing device of an embodiment of the present invention.

Fig. 2 is a partly enlarged view showing a state of picture image fixation in a fixing device of an embodiment of the present invention.

Fig. 3 is a partly enlarged view showing a state of picture image fixation in a conventional fixing device.

Fig. 4 is a partly enlarged view showing a state of picture image fixation in a conventional fixing device.

Fig. 5 is a partly enlarged view showing a state of picture image fixation in a conventional fixing device.

Fig. 6 is a sectional view of a conventional fixing device.

Description of the Reference Numerals

[0020]

101 Fixing roller (fixing member)

102 Press roller

103, 103a, 103b, 103c, 103d Surface layer material

104 Web

105a, 105b Core bar (base material)

106 Rubber elastic body (base material)

107 Heater

108 Web pressing roller

109 Web feed roller

110 Web take-up roller

111 Press roller surface layer

12 Recording material

13 Toner

Detailed Description of the Invention

[0021] The present invention relates to a fixing member with a film formed by applying a predetermined fluorine rubber composition to the fixing member surface at the fixing member for fixing a toner transferred onto a recording material. Since the predetermined fluorine rubber composition is disposed on the fixing member surface, numerous fine convex portions are formed on the fixing member surface.

[0022] The tips of the small convex portions formed on the fixing member surface layer are preferable to be smooth in shape. In the present embodiment, a spherical filler is filled into the surface layer material, and smooth convex portions are formed on the fixing member surface layer.

[0023] Since fine and smooth convex portions are formed on the fixing member surface layer, in fixing a toner transferred onto a recording material, the toner comes into contact with the convex portions on the fixing member surface layer via a lubricant. The toner on the recording material, after passing the fixing member, adheres to the recording material which is larger in contact area than the fixing member surface layer. Accordingly, the amount of the toner adhering to the fixing member surface is reduced, and generation of offset can be reliably prevented for a long period of time. As a result, the durability of the fixing member will be improved.

[0024] As solid content dispersed in the fluorine rubber composition, a reinforcing agent to strengthen the fluorine rubber composition and an antacid or the like to prevent generation of hydrogen fluoride in forming a film of the fluorine rubber composition are employed.

[0025] As a reinforcing agent, carbon black is generally employed. In the present embodiment, medium thermal carbon is used as a reinforcing agent. Medium thermal carbon is produced by contacting natural gas with a solid heated at high temperatures. Since the average grain size of medium thermal carbon in a state of being dispersed in a fluorine rubber composition is less than 5 μm , the surface of the fluorine rubber composition is increased in smoothness when the fluorine rubber composition is formed into a film.

[0026] As an antacid, divalent metal oxide and hydroxide such as magnesium oxide, zinc oxide, lead oxide, and calcium hydroxide are generally employed. Since the average grain size of an antacid in a state of being dispersed in a fluorine rubber composition is less than 5 μm , the surface of the fluorine rubber composition is increased in smoothness when the fluorine rubber composition is formed into a film.

[0027] As a proper method of measuring average grain size for filler grains, there is a laser diffracting grain distribution measuring method. The grain size of filler grains can be obtained by the theory of Fraunhofer diffraction with respect to diffracted patterns obtained by application of a laser beam to the grains. To obtain the average grain size, filler grains were diluted in a solvent, and the samples of fluorine rubber composition with the density of filler grains adjusted were passed through a measuring cell to obtain the size of grain passing through, and then the grain size most frequently corresponding to the obtained grain size was adopted as the average grain size.

[0028] The fluorine content of a fluorine rubber composition can be obtained by analyzing the components generated when the fluorine rubber composition is burnt at high temperatures.

[0029] A fluorine rubber composition of one embodiment of the present invention, used for the surface layer material of a fixing member to fix a toner transferred onto a recording material, comprises:

- (a) fluorine rubber having a polymerization degree based on vinylidene fluoride; and
- (b) at least one selected from the group consisting of a reinforcing agent, an antacid, a vulcanizing agent, a vulcanization accelerator, a spherical filler, and an organic solvent.

[0030] When a toner is fixed by using such fluorine rubber composition as the surface layer material of a fixing member, the adhesion of the toner to the surface of the fixing member is lowered, and accordingly, the amount of the toner sticking to the surface layer material of the fixing member is reduced. As a result, generation of offset can be prevented.

[0031] A fixing device of the present invention for fixing a toner transferred onto the surface of a recording material comprises:

- a fixing roller;
 - a press roller disposed opposing the fixing roller; and
 - a web to apply a lubricant to the surface of the fixing roller,
- wherein the fixing roller comprises a base material and a surface layer material disposed on the surface of the base material;
- the surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride; and
- a recording material having the toner transferred thereon passes between the fixing roller and the press roller while being pressed by the fixing roller and the press roller so that the surface layer material comes into contact with the toner, and thereby, the toner is fixed on the recording material.

[0032] By this configuration, when a toner is fixed, the adhesion of the toner to the surface of the fixing member is lowered, and accordingly, the amount of the toner sticking to the surface layer material of the fixing member is reduced. As a result, generation of offset can be prevented. Further, a fixing device having excellent durability can be obtained.

[0033] A fixing method of one embodiment of the present invention comprises:

- (a) a step of transferring a toner onto the surface of a recording material;
 - (b) a step of passing the recording material, having the toner transferred thereon, between a rotating fixing roller and press roller, under pressures applied by the fixing roller and the press roller,
- wherein the fixing roller comprises a base material and a surface layer material disposed on the surface of the base material;
- the recording material passes between the rollers in a manner such that the toner is positioned at the fixing roller side;
- the surface layer contains fluorine rubber having a polymerization degree based on vinylidene fluoride; and
- (c) a step of fixing the toner, pressed by the fixing roller and the press roller, on the surface of the recording material.

[0034] By this configuration, when a toner is fixed, the adhesion of the toner to the surface of the fixing member is lowered, and accordingly, the amount of the toner sticking to the surface layer material of the fixing member is reduced. As a result, generation of offset trouble can be prevented. Further, a fixing device having excellent durability can be obtained.

[0035] A method of manufacturing a fixing device of one embodiment of the present invention for fixing a toner transferred onto the surface of a recording material comprises the steps of:

- (a) manufacturing a fixing roller; and
- (b) manufacturing a press roller,

wherein the step of manufacturing the fixing roller comprises the steps of:

- (1) manufacturing a paint;

wherein the step of manufacturing the paint includes a step of mixing and dispersing fluorine rubber having a polymerization degree based on vinylidene fluoride, a vulcanizing agent, and a solvent;

- (2) applying the paint onto the surface of a base material having a spherical shape; and

- (3) drying and hardening the paint applied to the surface of the base material to form a surface layer material.

[0036] By this configuration, when a toner is fixed, the adhesion of the toner to the surface of the fixing member is lowered, and accordingly, the amount of the toner sticking to the surface layer material of the fixing member is reduced. As a result, generation of offset can be prevented. Further, a fixing device having excellent durability can be obtained.

[0037] Preferably, the fluorine rubber contains at least one copolymer selected from the group consisting of a copolymer of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene; a copolymer of tetrafluoroethylene, vinylidene fluoride and propylene; and a copolymer of vinylidene fluoride and hexafluoropropylene.

[0038] By this configuration, the advantage described above will be further enhanced.

[0039] Preferably, the copolymer contains fluorine in a range from 60 wt% to 70 wt%. This configuration will further enhance the advantage described above.

[0040] When the fluorine contained in the copolymer is less than 60 wt%, the advantage mentioned above will be slightly reduced. Also, when the fluorine content exceeds 70 wt%, a lubricant is hard to adhere to the surface of the fixing member. And consequently, the effect to prevent the toner from sticking to the surface of the fixing member will be slightly reduced.

[0041] Preferably, the fluorine rubber composition contains the reinforcing agent, and the reinforcing agent contains medium thermal carbon.

[0042] Preferably, the reinforcing agent is less than 5 μm in average grain size in a state of being dispersed in the surface layer material.

[0043] Thus, when the fluorine rubber composition is used for the surface layer material of a fixing member, the surface of the fixing member is increased in smoothness. Accordingly, the adhesion of the toner to the surface of the fixing member is lowered, and the amount of the toner sticking to the surface layer material of the fixing member is reduced. As a result, generation of offset can be prevented. That is, the surface layer material of the fixing member is increased in strength, and also, by reducing the average grain size of the reinforcing agent to be filled and further adding a spherical filler, it is possible to form fine convex portions on the fixing member surface. Further, in fixing a toner transferred onto a recording material, the toner is selectively fixed on the recording material having rougher surfaces, and thereby, generation of offset can be reliably prevented for a long period of time. As a result, the durability of the fixing roller will be improved.

[0044] Medium thermal carbon is smaller in specific surface area as compared with other carbon black such as channel black and furnace black. Therefore, it is less in the quantity of fluorine rubber composition required for wetting the surfaces of carbon black grains. Accordingly, it becomes possible to fill an increased amount of reinforcing agent when the reinforcing agent is dispersed in the fluorine rubber composition. Consequently, the surface layer material of the fixing member can be improved in strength by using medium thermal carbon.

[0045] The specific surface area of carbon black grain can be obtained by an adsorption process. A gas such as carbon dioxide or the like of which the molecular sectional area is known is adsorbed onto the surface of carbon black to cover the surface of the carbon black with monomolecular film of the gas. The specific surface area of the carbon black can be measured from the volume of the adsorbed gas.

[0046] When the average grain size of medium carbon black in a fluorine rubber composition exceeds 5 μm , and the fluorine rubber composition is used for the surface layer of a fixing member, then the surface of the fixing member will increase in roughness. As a result, the advantage described above will be slightly lessened.

[0047] Preferably, a fluorine rubber composition contains the reinforcing agent, and the reinforcing agent is contained in a range from 20 parts to 40 parts by weight as against 100 parts by weight of the fluorine rubber.

[0048] By this configuration, a film having an appropriate strength can be obtained when the fluorine rubber composition is used for the surface layer of a fixing member. Accordingly, even in case of fixing for a long period of time, the surface of the fixing member will be less in wear and abrasion. Also, generation of offset can be prevented. That is, the surface layer material of the fixing member is given an appropriate strength. Also, fine convex portions can be formed on the surface of the fixing member by adding a spherical filler. When fixing a toner transferred onto a recording material, the toner is selectively fixed on the recording material having rougher surfaces, and thereby, generation of offset can be reliably prevented for a long period of time. As a result, the durability of the fixing roller will be improved.

[0049] When the quantity of medium thermal carbon is less than 20 parts by weight as against 100 parts by weight of fluorine rubber composition, and the fluorine rubber composition is used for the surface layer of a fixing member, then the film coat will increase a little in softness. Therefore, in case of fixing for a long period of time, the fixing member surface wears down a little, and thereby, the above advantage will be slightly lessened.

[0050] Also, when the quantity of medium thermal carbon exceeds 40 parts by weight as against 100 parts by weight of fluorine rubber composition, the film coat of the surface layer material of the fixing member becomes slightly brittle, and in case of fixing for a long period of time, the fixing member surface wears down a little, and the advantage described above will be slightly lessened.

[0051] Preferably, the fluorine rubber composition contains the antacid, and the antacid contains at least one of divalent metal oxide and hydroxide.

[0052] By this configuration, in hardening the fluorine rubber composition, generation of hydrogen fluoride is prevented, and thereby, hardening of the fluorine rubber composition will be promoted. In this way, the fluorine rubber composition may be sufficiently hardened. As a result, it is possible to obtain a surface layer of a fixing member which ensures excellent durability. That is, when drying the surface layer material of the fixing member, hardening of the surface layer material will be promoted. The surface layer material of the fixing member is increased in strength. Also, by reducing the average grain size of the reinforcing agent to be filled and further adding a spherical filler, fine convex portions can be formed on the fixing member surface. Therefore, when fixing a toner transferred onto a recording material, the toner is selectively fixed on the recording material having rougher surfaces, and generation of offset can be reliably prevented for a long period of time, thereby improving the durability of the fixing roller.

[0053] Preferably, the antacid is less than 5 μm in average grain size in a state of being dispersed in the surface layer material.

[0054] By this configuration, when the fluorine rubber composition is used for the surface layer of a fixing member, the fixing member surface is increased in smoothness. As a result, in fixing a toner, it is possible to lower the adhesion of the toner to the fixing member surface, and thereby, generation of offset can be prevented.

[0055] Preferably, the antacid is contained in a range from 5 parts to 20 parts by weight as against 100 parts by weight of the fluorine rubber.

[0056] When the quantity of antacid is less than 5 parts by weight as against 100 parts by weight of fluorine rubber composition, and the fluorine rubber composition is used for the surface layer material of a fixing member, then the fluorine rubber composition is not sufficiently hardened, causing the film coat of the surface layer material is increased in softness. Accordingly, in case of fixing for a long period of time, the fixing member surface wears down a little. As a result, the above advantage will be slightly lessened.

[0057] Also, when the quantity of antacid exceeds 20 parts by weight as against 100 parts by weight of fluorine rubber composition, and the fluorine rubber composition is used for the surface layer material of a fixing member, then the film coat of the surface layer becomes brittle, and in case of fixing for a long period of time, the fixing member surface wears down a little. As a result, the advantage described above will be slightly lessened.

[0058] Preferably, the fluorine rubber composition contains a vulcanizing agent, and the vulcanizing agent contains at least one of polyol type compound and amine type compound.

[0059] By this configuration, the fluorine rubber composition can be sufficiently hardened. As a result, it is possible to obtain a surface layer material of a fixing member having excellent durability.

[0060] As a polyol type vulcanizing agent, all of commonly known compounds used for polyol vulcanization of copolymer can be used. Particularly, aromatic hydroxy compounds such as bisphenol AF, bisphenol A, or hydroquinone are preferably to be used as a polyol type vulcanizing agent.

[0061] As an amine type vulcanizing agent, all of commonly known compounds used for amine vulcanization of vinylidene fluoride type copolymer can be used. Particularly, hexamethylene diamine, hexamethylene diamine dicarbamate, dicinnamylidene hexamethylene diamine, etc. are preferable to be used as an amine vulcanizing agent.

[0062] Preferably, the fluorine rubber composition contains a vulcanizing agent, and the vulcanizing agent is contained in a range from 0.5 part to 5 parts by weight as against 100 parts by weight of the fluorine rubber.

[0063] By this configuration, the fluorine rubber composition can be sufficiently hardened. As a result, it is possible to obtain a surface layer material of a fixing member having excellent durability.

[0064] When the quantity of vulcanizing agent is less than 0.5 part by weight as against 100 parts by weight of fluorine rubber composition, the fluorine rubber composition is not sufficiently hardened. Accordingly, the above advantage will be slightly lessened.

[0065] Also, when the quantity of vulcanizing agent exceeds 5 parts by weight as against 100 parts by weight of fluorine rubber composition, and the fluorine rubber composition is used for the fixing member surface layer, then the film coat becomes brittle. Accordingly, in case of fixing for a long period of time, the fixing member surface wears down a little. As a result, the advantage described above will be slightly lessened.

[0066] Preferably, the fluorine rubber composition contains the vulcanization accelerator, and the accelerator contains at least one of organic quaternary phosphonium salt and organic quaternary ammonium salt.

[0067] By this configuration, hardening of the fluorine rubber composition can be promoted. Accordingly, it is possible to obtain a surface layer material of a fixing member having excellent durability.

[0068] As an unsaturated multifunctional compound, it is preferable to use triallylisocyanulate, triallylcyanulate, trimethylol propane trimethacrylate, polybutadiene, etc.

[0069] As an organic salt used as a vulcanization accelerator, it is preferable to use tetrabutyl ammonium acid sulfate, tetrabutyl ammonium bromide, 8-benzyl-1, 8-diazabicyclo [5. 4. 0.] undeca-7-enium chloride, P-toluenesulfonic acid 1, 8-diazabicyclo [5. 4. 0.] undeca-7-enium, tetrabutylphosphonium chloride, trioctylmethyl phosphonium chloride, triphenyl benzyl phosphonium chloride, 1,8-diazabicyclo [5. 4. 0.] undeca-7-salt, pyridine, tributylamine, triphenylphosphine, tributylphosphite, etc.

[0070] Preferably, the vulcanization accelerator is contained in a range from 0.5 part to 5 parts by weight as against 100 parts by weight of the fluorine rubber composition.

[0071] By this configuration, the fluorine rubber composition can be sufficiently hardened. As a result, it is possible to obtain a surface layer material of a fixing member having excellent durability.

[0072] When the quantity of vulcanization accelerator is less than 0.5 part by weight as against 100 parts by weight of fluorine rubber composition, the fluorine rubber composition is not sufficiently hardened. Accordingly, the above advantage will be slightly lessened.

[0073] Also, when the quantity of vulcanization accelerator exceeds 5 parts by weight as against 100 parts by weight of fluorine rubber composition, and the fluorine rubber composition is used for the fixing member surface layer, then the film coat becomes brittle. Accordingly, in case of fixing for a long period of time, the fixing member surface wears down a little. As a result, the advantage described above will be slightly lessened.

[0074] Preferably, the fluorine rubber composition contains a spherical filler, and the spherical filler is over 80% in sphericity.

[0075] Still preferably, the spherical filler ranges from 0.5 μm to 10 μm in average grain size.

[0076] By this configuration, when the fluorine rubber composition is applied onto the surface of a fixing member and dried, spherical convex portions can be formed on the surface of the fixing member. Therefore, when a toner is fixed, the contact area of the toner adhering to the fixing member surface is decreased. Accordingly, the adhesion of the toner sticking to the fixing member is lowered, and also the amount of the toner sticking to the fixing member is reduced. As a result, generation of offset can be prevented.

[0077] When the major axis and minor axis of the relevant grain are "A" and "B" respectively, the sphericity (%) of the spherical filler can be represented by $\{1-(|A-B|)/(A+B)/2\} \times 100(\%)$. The grain size is measured through a process of taking photos of the relevant grain by an optical or electronic microscope and a process of measuring the size of the photographed grain.

[0078] In case the sphericity of the spherical filler is less than 80%, spherical convex portions will not be formed on the surface of the fixing member. Accordingly, in toner fixing, the effect to reduce the contact area of the toner coming into contact with the fixing member surface is decreased. As a result, the above advantage will be slightly lessened.

[0079] In case the average grain size of the spherical filler is less than 0.5 μm , it is not possible to form spherical convex portions on the surface of the fixing member. Therefore, in toner fixing, the contact area of the toner coming into contact with the fixing member surface cannot be reduced. As a result, the above advantage will be slightly lessened.

[0080] When the average grain size of the spherical filler exceeds 10 μm , and it is used for the surface of a fixing member, then the spherical convex portions obtained will become larger. Therefore, in toner fixing, the toner coming into contact with the fixing member surface will get into gaps between convex portions. Accordingly, the toner is hard to adhere to the fixing member surface. As a result, the above advantage will be slightly lessened.

[0081] Preferably, the spherical filler is contained in a range from 5 parts to 30 parts by weight as against 100 parts by weight of the fluorine rubber.

[0082] By this configuration, when the fluorine rubber composition is applied onto the surface of a fixing member and dried, spherical convex portions can be formed on the surface of the fixing member. Therefore, in toner fixing, the contact area of the toner coming into contact with the fixing member surface is reduced. Accordingly, the adhesion of the toner sticking to the fixing member is lowered, and the amount of the toner sticking to the fixing member is decreased. As a result, generation of offset can be prevented.

[0083] When the quantity of spherical filler is less than 5 parts by weight as against 100 parts by weight of fluorine rubber composition, the number of spherical convex portions formed on the surface of the fixing member is reduced. As a result, the above advantage will be slightly lessened.

[0084] Also, when the quantity of spherical filler exceeds 30 parts by weight as against 100 parts by weight of fluorine rubber composition, the film coat of the surface layer material of the fixing member becomes brittle, and in case of fixing for a long period of time, the fixing member surface wears down a little. As a result, the above advantage will be slightly lessened.

[0085] Preferably, the fluorine rubber composition includes an organic solvent, and the fluorine rubber composition

is dissolved in the organic solvent. Or, the reinforcing agent and the spherical filler are uniformly dispersed.

[0086] The organic solvent is used to change fluorine rubber composition into a paint. There is no special limitations on the type and quantity of the organic solvent used, and they can be properly selected according to the painting method. The organic solvent has a function to dissolve or disperse at least one selected from the group consisting of a reinforcing agent, antacid, vulcanizing agent, vulcanization accelerator, and spherical filler.

[0087] A fixing device of one embodiment of the present invention for fixing a toner transferred onto the surface of a recording material comprises a base material and a surface layer material disposed on the surface of the base material, and the surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride.

[0088] Since such fluorine rubber composition is used as the surface layer material of a fixing member, when a toner is fixed, the adhesion of the toner to the surface of the fixing member is lowered. Accordingly, the amount of the toner sticking to the surface layer material of the fixing member is reduced, and as a result, generation of offset can be prevented.

[0089] Preferably, the surface layer material has numerous fine convex portions.

[0090] By this configuration, when a toner is fixed, the contact area of the toner coming in contact with the surface of the fixing member is decreased. Therefore, the adhesion of the toner sticking to the fixing member is lowered, and also, the amount of the toner sticking to the fixing member is reduced. As a result, the above advantage will be further enhanced.

[0091] Preferably, each convex portion of the numerous fine convex portions has a spherical tip.

[0092] By this configuration, when a toner is fixed, the contact area of the toner coming into contact with the fixing member surface is decreased. As a result, the above advantage will be further enhanced.

[0093] Preferably, the surface layer material is less than 5 μm in surface roughness (R_z).

[0094] By this configuration, when a toner is fixed, the contact area of the toner coming in contact with the fixing member surface is decreased. Accordingly, the adhesion of the toner adhering to the fixing member is lowered. As a result, the above advantage will be further enhanced.

[0095] Surface roughness " R_z " is to be a standard for evaluating the surface roughness mentioned in 34. Metal surface treatment of JIS Handbook. The profile curve is measured by a surface roughness meter of contact type, etc. From the profile curve, the maximum height average value of elevation is measured with respect to the peaks from the highest to the fifth highest measured in the direction of longitudinal magnification from the straight line, being parallel to the average line and not traversing the profile curve, at a portion with only the standard length removed. Further, the maximum depth average value of elevation is measured with respect to the bottoms from the deepest to the fifth deepest. The difference between the maximum height average value and the maximum depth average value is measured on a micro-meter unit.

[0096] When the surface roughness " R_z " of a fixing member exceeds 5 μm , the surface of the fixing member is increased in roughness. Therefore, when a toner is fixed, the toner is hard to adhere to the fixing member surface due to anchor effect. As a result, the above advantage will be slightly lessened.

[0097] Preferably, the fine convex portions are formed in a range from 5,000 pieces to one million pieces per square millimeter.

[0098] By this configuration, the adhesion of the toner sticking to the fixing member is further decreased. As a result, the above advantage will be further enhanced.

[0099] An electronic microscope is used for counting the number of convex portions on the surface of a fixing member. A piece of surface layer material of about a few square millimeters is cut out of a fixing member surface, and the material is photographed and observed by using an electronic microscope. A microscope of about 1,000 to 10,000 magnifications is employed. The number of convex portions existing in an area from 10 μm sq. to 1 μm sq. of the fixing member surface is counted.

[0100] The toner fixed is softened due to heat and squeezed by pressures. Therefore, the squeezed toner comes into contact with the recording material or fixing member surface in larger area as compared to the original grain size. In that case, when the number of the convex portions on the surface of the fixing member is less than 5,000 pieces per square millimeter, the toner will come into contact with areas without convex portions on the surface of the fixing member. Accordingly, some of the toner touches the surface of the fixing member, and as a result, the effect to prevent generation of offset will be slightly lessened.

[0101] Also, when the number of convex portions exceeds 5 million pieces per square millimeter, the fixing member surface becomes nearly flat. Therefore, the contact area between the fixing member and the toner is increased. Accordingly, the adhesion of the toner sticking to the surface of the fixing member is increased. As a result, the above advantage will be slightly lessened.

[0102] An exemplary embodiment of the present invention will be described in the following.

[0103] Fig. 1 is a sectional view of a fixing device of an exemplary embodiment of the present invention. The fixing device shown in Fig. 1 comprises a fixing roller having a surface layer material formed of a predetermined fluorine

rubber composition on the surface of the fixing member. The detail of a member by which the fixing member is configured will be described in the following.

[0104] As shown in Fig. 1, the fixing device comprises a fixing roller 101, a press roller 102, and a web 104. The fixing roller 101 serves to fix a toner 13 transferred onto a recording material 12. The press roller 102 is arranged opposing to the fixing device 101. The web 104 serves to apply a lubricant such as silicone oil to prevent the toner from sticking to the surface of the fixing roller 101.

[0105] The fixing roller 101 comprises a core bar 105a made of aluminum, a rubber elastic body 106, and a surface layer material 103. The rubber elastic body 106 includes silicone resin and is coated over the core bar 105a made of aluminum by 2 mm in thickness. The surface layer material 103 includes a fluorine rubber composition. The surface layer material 103 is applied onto the rubber elastic body 106 and dried, after polishing the surface of the rubber elastic body 106. In this way, the fixing roller 101 of about 40 mm in outer diameter is formed. Fine convex portions are formed on the surface of the fixing roller 101. The surface roughness "Rz" of the fixing roller 101 is less than 5 μm . The number of fine convex portions are in a range from 5,000 pieces to 5 million pieces per square millimeter. Also, there is provided a heater 107 as a heat source in the core bar 105. The heater 107 is controlled so that the surface temperature of the fixing roller 101 is kept at about 140°C to 170°C.

[0106] The press roller 102 comprises a core bar 105b made of stainless steel, a rubber elastic body 106, and fluororesin (FLC) 111. The rubber elastic body 106 is coated over the core bar 105b by about 2 mm in thickness. The fluororesin 111 is coated over the rubber elastic body 106 by 30 μm in thickness. In this way, the press roller 102 of about 40 mm in outer diameter is formed.

[0107] The web 104 includes a base material and a lubricant impregnated in the base material. The base material includes polyester non-woven cloth and PTFE (fluororesin) affixed to the non-woven cloth. The shape of the web 104 is 60 μm thick, 220 mm wide, and 800 mm long. The web 104 is taken up from a web feed roller 109 onto a web take-up roller 110 at a predetermined speed. In that case, the web 104 is pressed against the fixing roller 101 by the web pressing roller 108, and then, a lubricant impregnated in the web 104 is applied onto the fixing roller 101. In this way, a lubricant is applied to the fixing roller 101 during the fixing operation. Thus, the toner 13 is prevented from sticking to the fixing roller 101.

[0108] A film of a predetermined fluorine rubber composition is disposed on the surface layer material 103 of the fixing roller so that the toner 13 will not easily adhere to the surface layer material 103 of the fixing roller. The film is formed on the surface layer material 103 of the fixing roller by applying and drying a predetermined fluorine rubber composition.

[0109] A fluorine rubber composition contains fluorine rubber (component A), reinforcing agent (component B), antacid (component C), vulcanizing agent (component D), vulcanization accelerator (component E), spherical filler (component F), and organic solvent (component G). The fluorine rubber (component A) contains at least a polymerization degree of vinylidene fluoride.

[0110] The fluorine rubber (component A) contains at least one of a copolymer of tetrafluoroethylene/vinylidene fluoride/hexafluoropropylene, a copolymer of tetrafluoroethylene/vinylidene fluoride/propylene, and a copolymer of vinylidene/hexafluoropropylene. It is preferable to contain the fluorine rubber (component A) by 60 wt% to 70 wt% as against 100 wt% of fluorine rubber composition. Thus, it is possible to obtain a fixing member having excellent toner parting properties.

[0111] Preferably, the reinforcing agent (component B) contains medium thermal carbon. The reinforcing agent is dispersed in the fluorine rubber composition, and has an average grain size of less than 5 μm in a state of being dispersed. Also, the quantity of reinforcing agent (component B) to be applied is in a range from 20 parts to 40 parts by weight as against 100 parts by weight of fluorine rubber (component A). By this configuration, the surface layer material 103 whose surface roughness (Rz) is less than 5 μm can be obtained. Further, it is possible to obtain a fixing member having a film strength that may withstand a long-time fixing.

[0112] Preferably, the antacid (component C) contains bivalent metal oxide or hydroxide. The antacid is dispersed in the fluorine rubber composition, and has an average grain size of less than 5 μm in a state of being dispersed. Also, the quantity of antacid (component C) to be applied is in a range from 5 parts to 20 parts by weight as against 100 parts by weight of fluorine rubber (component A). By this configuration, the surface layer material 103 whose surface roughness (Rz) is 5 μm or less can be obtained. Further, it is possible to obtain a fixing member having a film strength that may withstand a long-time fixing.

[0113] Preferably, the vulcanizing agent (component D) contains a polyol or amine type vulcanizing agent. Also, the amount of vulcanizing agent (component D) to be added is in a range from 0.5 part to 5 parts by weight as against 100 parts by weight of fluorine rubber (component A). By this configuration, the surface layer material 103 is sufficiently hardened. As a result, it is possible to obtain a fixing member having a film strength that may withstand a long-time fixing.

[0114] Preferably, the vulcanization accelerator (component E) contains organic quaternary phosphonium salt or organic quaternary ammonium salt. Also, the amount of vulcanization accelerator (component E) to be added is in a range from 0.5 part to 5 parts by weight as against 100 parts by weight of fluorine rubber (component A). By this

configuration, the surface layer material 103 is sufficiently hardened. As a result, it is possible to obtain a fixing member having a film strength that may withstand a long-time fixing.

[0115] Preferably, the spherical filler (component F) is a spherical filler having sphericity of over 80% and an average grain size ranging from 0.5 μm to 10 μm . Also, the amount of spherical filler (component F) to be filled is in a range from 5 parts to 30 parts by weight as against 100 parts by weight of fluorine rubber (component A). By this configuration, fine convex portions having spherical tips can be easily formed on the surface of the surface layer material 103. Further, the surface layer material 103 thus formed is as smooth as less than 5 μm in surface roughness (R_z).

[0116] The surface layer material is applied onto the rubber elastic body 106 and is dried. In this way, the surface layer material 103 of a fixing roller having numerous fine convex portions is formed. The surface layer material contains spherical grains of 0.5 μm to 10 μm in average grain size, in the ratio of 5 to 50 vol% of fill. Since the surface layer material 103 of the fixing roller has numerous fine convex portions, the toner 13 can be prevented from sticking to the surface of the surface layer material 103 of the fixing roller. As spherical grain as a filler, resin powder (silicone rubber powder, nylon powder, acryl powder, etc.), metallic powder (iron, copper, aluminum, etc.), and ceramic powder (alumina, silica, zirconia, etc.) may be used. However, it is necessary to use these spherical grains according to the types of the surface layer material of the fixing roller. In case the filler has bad wettability that affects the surface layer material, the filler will not be uniformly dispersed in the surface layer material, and fine convex portions cannot be formed. In case the filler is too great in specific gravity as compared with the surface layer material, the filler will go to the bottom of the surface layer material, and fine convex portions cannot be formed on the surface of the surface layer material 103. Also, in case the filler is too small in specific gravity, the filler will go up to the surface of the surface layer material, and fine convex portions cannot be formed on the surface of the surface layer material 103. Accordingly, it is necessary to select a suitable filler for the surface layer material in order to obtain fine convex portions having the desired shape.

[0117] As described above, since a fluorine rubber composition is disposed on the surface layer of a fixing member, when the toner 13 transferred onto the recording material 12 is fixed, the toner 13 comes into contact with convex portions of the surface layer material 103 via a lubricant. And, after the toner 13 on the recording material 12 has passed the fixing member, the toner 13 adheres to the surface of the recording material 12 larger in contact area than the surface layer of the fixing member. Therefore, the amount of toner 13 adhering to the fixing member surface is reduced. Thus, generation of offset can be reliably prevented for a long period of time. As a result, the durability of the fixing member will be improved.

[0118] The effect of a predetermined fluorine rubber composition disposed on the surface layer of a fixing roller as a fixing member will be described with reference to Fig. 2 to Fig. 5.

[0119] Fig. 2 is a partly enlarged view showing a state of picture image fixation in a fixing device of one embodiment of the present invention. Fig. 3, Fig. 4 and Fig. 5 are partly enlarged views showing a state of picture image fixation in a conventional fixing device.

[0120] In Fig. 3, fixing roller 201 has surface layer material 103b having a smooth surface without fine convex portions. Fig. 3 shows how the toner 13 is fixed on the recording material 12 by using surface layer material 103b without fine convex portions. When the toner 13 passes underneath the fixing roller 201, the toner 13 is squeezed by heat and pressure of the fixing roller 201. After the toner 13 has passed underneath the fixing roller 201, most of the toner 13 is fixed on the recording material 12, but some of the toner 13 sticks to the surface layer material 103b of the fixing roller. When the toner 13 sticking to the surface layer material 103b of the fixing roller comes into contact with the next recording material 12, some of the toner 13 sticks onto the next recording material 12, thereby causing generation of offset.

[0121] In Fig. 4, the surface layer material 103c of fixing roller 201 exceeds 5 μm in surface roughness (R_z). Fig. 4 shows how the toner 13 is fixed on the recording material 12 by using the fixing roller 201 with such high surface roughness of surface layer material 103c. The average grain size of toner 13 is in a range from about 10 μm to about 15 μm , and the toner 13 on the recording material 12 comes into contact with the surface of surface layer material 103c via a lubricant.

[0122] When the toner 13 passes underneath the fixing roller 201, the toner 13 is squeezed by heat and pressure of the fixing roller. Then, the toner 13 comes into contact with the surface of the surface layer material 103c having surface roughness (R_z) of over 5 μm . Therefore, some of the toner 13 sticks to the surface layer material 103c due to anchor effect. When the toner 13 sticking to the surface layer material 103c of the fixing roller comes into contact with the next recording material 12, some of the toner 13 sticks onto the recording material 12, thereby causing generation of offset.

[0123] In Fig. 5, the surface of surface layer material 103d of the fixing roller includes fine convex portions having sharp tips. Fig. 5 shows how the toner 13 is fixed on the recording material 12 by using the fixing roller with the surface layer material 103d having such fine convex portions with sharp tips. The average grain size of toner 13 ranges from about 10 μm to about 15 μm , and the toner 13 on the recording material 12 comes into contact with the surface of surface layer material 103d via a lubricant.

[0124] When the toner 13 passes underneath the fixing roller 201, the toner 13 is squeezed by heat and pressure

of the fixing roller 201. Then, the toner 13 comes into contact with the surface of the surface layer material 103d having fine convex portions with sharp tips. Therefore, some of the toner 13 sticks to the surface layer material 103d due to anchor effect. When the toner 13 sticking to the surface layer material 103d of the fixing roller comes into contact with the next recording material 12, some of the toner 13 sticks onto the recording material 12, thereby causing generation of offset.

[0125] Fig. 2 is a partly enlarged view showing a state of picture image fixation in a fixing device of one embodiment of the present invention. In Fig. 2, surface layer material 103a is disposed on the surface of fixing roller 101. The surface layer material 103a has fine convex portions, and the fine convex portions have spherical tips. Fig. 2 shows how the toner 13 is fixed on the recording material 12 by using the fixing roller 101 with the surface layer material 103a having such fine convex portions. The surface layer material 103a having fine convex portions with sharp tips is formed on the surface of fixing roller 101, and the toner 13 transferred onto the recording material 12 is fixed, then the toner 13 comes into contact with the convex portions of surface layer material 103a via a lubricant. After the toner 13 on the recording material 12 has passed the fixing member, the toner 13 sticks onto the recording material 12 larger in contact area than the surface layer material 103a. Accordingly, the amount of the toner sticking to the surface layer material 12 is reduced. As a result, generation of offset can be reliably prevented for a long period of time. Further, the durability of the fixing device will be improved.

[0126] As described above, fine convex portions with spherical tips are formed on the surface of the surface layer material of the fixing roller. Preferably, the number of convex portions is in a range from 5,000 pieces to one million pieces per square millimeter, and the surface roughness (Rz) of the surface layer material is less than 5 μm . Therefore, when the toner transferred onto the recording material is fixed, the toner comes into contact, in less contact area, with the surface layer of the fixing member having excellent parting properties. After the toner on the recording material has passed the fixing member, the toner sticks onto the recording material larger in contact area than the surface layer of the fixing member. Accordingly, the amount of the toner sticking to the fixing member surface is reduced. As a result, generation of offset can be reliably prevented for a long period of time. Further, the durability of the fixing member will be improved.

Exemplary Embodiment:

[0127] An exemplary embodiment of the present invention will be described in the following.

[0128] As a surface layer material of a fixing roller, a fluorine rubber composition having the following configuration was prepared.

(Component A) Fluorine rubber:

Ternary fluorine rubber, a copolymer of vinylidene fluoride, tetrafluoroethylene, and hexafluoropropylene.

(100 parts by weight)

(Component B) Reinforcing agent:

Medium thermal carbon. (X1 part by weight)

(Component C) Antacid:

Magnesium oxide. (X2 parts by weight)

(Component D) Vulcanizing agent:

Bisphenol FA. (X3 parts by weight)

(Component E) Vulcanization accelerator:

Tetrabutyl ammonium bisulfate. (X4 parts by weight)

(Component F) Spherical filler:

Spherical silica or glass beads. (X5 parts by weight)

(Component G) Organic solvent:

Butyl acetate. (400 parts by weight)

[0129] A method of preparing a paint for surface layer material will be described in the following.

[0130] Three types of fluorine rubber "A1", "A2" and "A3" were prepared by an emulsion polymerization method: the fluorine rubber is a ternary copolymer consisting of vinylidene fluoride, tetrafluoroethylene, and hexafluoropropylene. The fluorine content of each fluorine rubber was measured. The results of the measurement are as follows: fluorine rubber "A1" contained fluorine by 60%, fluorine rubber "A2" contained fluorine by 65%, and fluorine rubber "A3" contained fluorine by 70%.

[0131] Also, fluorine rubber "A4" was prepared by an emulsion polymerization method: the fluorine rubber consists of vinylidene fluoride, tetrafluoroethylene, and propylene. The fluorine content of the prepared fluorine rubber was measured. Fluorine rubber "A4" contained fluorine by 55%.

EP 1 160 284 A2

(Component A): 100 parts by weight of any one of the four types of fluorine rubber "A1", "A2", "A3", "A4".

(Component B): X1 part by weight of medium thermal carbon (Huber's N - 907) as a reinforcing agent.

(Component C): X2 parts by weight of magnesium oxide (Kyowa Chemical's Kyowa Mag 150) as an antacid.

(Component D): X3 parts by weight of bisphenol AF as a vulcanizing agent.

(Component E): X4 parts by weight of tetrabutyl ammonium bisulfate as a vulcanization accelerator.

(Component F): X5 parts by weight of spherical silica with 99% sphericity (Admatec's Adma Fine) or glass beads with 99% sphericity (Toshiba Balotini's Hollow Glass Beads) or amorphous silica with 70% sphericity (Fuji Silicia Chemical's Cylicia) as a spherical filler.

[0132] The above components A, B, C, D, E, and F were mixed and dispersed in a roller mill disperser to prepare a mixture.

[0133] When the components were mixed and dispersed in a roller mill, various mixtures different in filler grain size were obtained by changing the operation time. Subsequently, the mixtures thus obtained were dissolved in the organic solvent (component F), 400 parts by weight of butyl acetate. In this way, various fluorine rubber compositions were obtained.

[0134] The features of various spherical fillers "F1", "F2", "F3", "F4", "F5" used in the present exemplary embodiment are shown in Table 1.

Table 1

No.		Contents	Product No.	Sphericity %	Average grain size μm
Spherical filler	F1	Spherical silica	SO-C3	99	1
	F2	Spherical silica	SO-C1	99	0.3
	F3	Glass beads	HSC110	99	10
	F4	Glass beads	GB301S	99	45
	F5	Amorphous silica	310	70	1.4

[0135] A method of forming the surface layer material of a fixing roller is described in the following.

[0136] First, a silicone rubber elastic body is formed on a core bar of a fixing roller. The surface of the formed silicone rubber elastic body is polished, and then, cleaned. Next, each of the fluorine rubber compositions thus formed is sprayed and coated onto the surface of a silicone rubber elastic body, and is left at the room temperature for two hours. In this way, butyl acetate used as an organic solvent is dispersed. Subsequently, it is dried in an oven at 80°C for two hours, and further, dried in the oven at 200°C for one hour. Thus, fixing rollers having different surface layer materials were manufactured.

[0137] The fixing tests were carried out by using each of the fixing rollers manufactured in this way. The fixing tests were performed with respect to the examples and the comparative examples. The test results were evaluated by the number of sheets subjected to fixing tests until generation of offset. Incidentally, the number of sheets to be tested is 60,000 sheets max.

[0138] As a printer used for the tests, a color laser printer of Matsushita Electric Ind., Ltd. was employed. As a recording material, NIP paper (Kobayashi Kirokushi Co., Ltd.) of A4 size was used under the fixing test condition. Also, the fixing temperature (fixing roller surface temperature) is 160°C, and the fixing speed is 4 ppm (4 sheets/min.). The toner used is a product of Kao Soap Co., Ltd., which contains polyester resin as base resin and is 12 μm in average grain size. The printing pattern is a 5% random pattern. Also, as a lubricant, amino denatured dimethyl polycyloxane (The Shin-etsu Chemical's) whose grain size is 1,000 cps at 25°C was employed.

[0139] The results of the fixing tests are described with respect to the specific examples and comparative examples.

Example 1:

[0140] A paint of fluorine rubber composition was prepared by using fluorine rubber "A1" of fluorine content 60%. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 2:

[0141] A paint of fluorine rubber composition was prepared by using fluorine rubber "A2" of fluorine content 65%.

The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 3:

[0142] A paint of fluorine rubber composition was prepared by using fluorine rubber "A3" of fluorine content 70%. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 4:

[0143] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 20 parts by weight of reinforcing agent (component B) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 3 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 5:

[0144] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 40 parts by weight of reinforcing agent (component B) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 6:

[0145] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 5 parts by weight of antacid (component C) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 7:

[0146] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 20 parts by weight of antacid (component C) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 8:

[0147] A paint of fluorine rubber composition was prepared by using fluorine rubber "A2" of fluorine content 65%. In the process of preparing the paint, the operation time for dispersion by a roller mill disperser was shortened. The average grain size of the filler contained in the prepared paint was 4 μm , and the surface roughness (Rz) of the fixing roller was 5 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 9:

[0148] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 0.5 parts by weight of vulcanizing agent (component D) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 10:

[0149] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 5 parts by weight of vulcanizing agent (component D) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 11:

[0150] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 0.5 parts by weight of vulcanization accelerator (component E) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 12:

[0151] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 5 parts by weight of vulcanization accelerator (component E) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 13:

[0152] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 5 parts by weight of spherical filler (F1) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 50,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 14:

[0153] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 30 parts by weight of spherical filler (F1) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was one million pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 15:

[0154] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 15 parts by weight of spherical filler (F3) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 5 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 20,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Example 16:

[0155] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 5 parts by weight of spherical filler (F3) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 5 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 5,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 60,000 sheets.

Comparative Example 1:

[0156] A paint of fluorine rubber composition was prepared by using fluorine rubber "A4" of fluorine content 55%. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, generation of offset was observed in fixing tests on 5,000 sheets.

Comparative Example 2:

[0157] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 15 parts by weight of reinforcing agent (component B) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, generation of offset was observed in fixing tests on 30,000 sheets.

Comparative Example 3:

[0158] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 45 parts by weight of reinforcing agent (component B) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, generation of offset was observed in fixing tests on 15,000 sheets.

Comparative Example 4:

[0159] A paint of fluorine rubber composition was prepared by using fluorine rubber "A2" of fluorine content 65%. In the process of preparing the paint, the operation time for dispersion by a roller mill disperser was shortened. The average grain size of the filler contained in the prepared paint was 8 μm , and the surface roughness (Rz) of the fixing roller was 15 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 10,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 5,000 sheets.

Comparative Example 5:

[0160] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 3 parts by weight of antacid (component C) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, generation of offset was observed in fixing tests on 15,000 sheets.

Comparative Example 6:

[0161] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 25 parts by weight of antacid (component C) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, generation of offset was observed in fixing tests on 30,000 sheets.

Comparative Example 7:

[0162] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 0.2 part by weight of vulcanizing agent (component D) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (Rz) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 5,000 sheets.

Comparative Example 8:

[0163] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content

EP 1 160 284 A2

65% and 7 parts by weight of vulcanizing agent (component D) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (R_z) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 40,000 sheets.

Comparative Example 9:

[0164] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 0.2 part by weight of vulcanization accelerator (component E) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (R_z) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 10,000 sheets.

Comparative Example 10:

[0165] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 7 parts by weight of vulcanization accelerator (component E) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (R_z) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 250,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 45,000 sheets.

Comparative Example 11:

[0166] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 15 parts by weight of spherical filler (F4) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (R_z) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was two million pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 10,000 sheets.

Comparative Example 12:

[0167] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 15 parts by weight of spherical filler (F4) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (R_z) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 2,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 5,000 sheets.

Comparative Example 13:

[0168] A paint of fluorine rubber composition containing 100 parts by weight of fluorine rubber "A2" of fluorine content 65% and 15 parts by weight of spherical filler (F5) was prepared. The average grain size of the filler contained in the prepared paint was 2 μm , and the surface roughness (R_z) of the fixing roller was 4 μm . The number of convex portions on the fixing roller surface, observed by an electronic microscope, was 100,000 pieces. As a result of the fixing test, no generation of offset was observed in fixing tests on 2,000 sheets.

[0169] The paint configuration and properties of the fluorine rubber composition used for the examples, and the features of film coat of fluorine rubber composition, and the test results are shown in Table 2, 3, and 4.

EP 1 160 284 A2

Table 2

			1	2	3	4	5	6
Paint configuration	Fluorine rubber	A1	100					
		A2		100		100	100	100
		A3			100			
		A4						
	Reinforcing agent B		30	30	30	20	40	30
	Antacid C		10	10	10	10	10	5
	Vulcanizing agent D		2	2	2	2	2	2
	Vulcanization accelerator E		2	2	2	2	2	2
	Spherical filler	F1	15	15	15	15	15	15
		F2						
		F3						
		F4						
	Organic solvent G							
		400	400	400	400	400	400	
Properties	Average grain size μm		2	2	2	2	2	2
Features of film coat	Surface roughness Rz μm		4	4	4	4	4	4
	Number of convex portions 1,000 pcs/mm ²		250	250	250	250	250	250
Number of sheets tested			60k	60k	60k	60k	60k	60k

Table 3

			7	8	9	10	11	12
35	Paint configuration	Fluorine rubber	A1					
			A2	100	100	100	100	100
			A3					
			A4					
40		Reinforcing agent B		30	30	30	30	30
		Antacid C		20	10	10	10	10
		Vulcanizing agent D		2	2	0.5	5	2
45		Vulcanization accelerator E		2	2	2	2	0.5
50		Spherical filler	F1	15	15	15	15	15
			F2					
			F3					
			F4					
			F5					
		Organic solvent F		400	400	400	400	400
55	Properties	Average grain size μm		2	2	2	2	2

EP 1 160 284 A2

Table 3 (continued)

		7	8	9	10	11	12
Features of film coat	Surface roughness Rz μm	4	4	4	4	4	4
	Number of convex portions 1,000 pcs/mm ²	250	250	250	250	250	250
Number of sheets tested		60k	60k	60k	60k	60k	60k

Table 4

			13	14	15	16
Paint configuration	Fluorine rubber	A1				
		A2	100	100	100	100
		A3				
		A4				
	Reinforcing agent B		30	30	30	30
	Antacid C		20	10	10	10
	Vulcanizing agent D		2	2	2	2
	Vulcanization accelerator E		2	2	2	2
	Spherical filler	F1	5	30		
		F2				
		F3			15	5
		F4				
		F5				
	Organic solvent F		400	400	400	400
	Properties	Average grain size μm	2	2	2	2
	Features of film coat	Surface roughness Rz μm	4	4	5	5
		Number of convex portions 1,000 pcs/mm ²	50	1000	20	5
	Number of sheets tested		60k	60k	60k	60k

[0170] The paint configuration and properties of the fluorine rubber used for the comparative examples, and the features of film coat of fluorine rubber composition, and the test results. are shown in Table 5 and 6.

Table 5

			CE1	CE2	CE3	CE4	CE5	CE6	
5	Paint configuration	Fluorine rubber	A1						
			A2		100	100	100	100	100
			A3						
			A4	100					
10		Reinforcing agent B		30	15	45	30	30	35
		Antacid C		10	15	15	15	3	25
		Vulcanizing agent D		2	2	2	2	2	2
15		vulcanization accelerator E		2	2	2	2	2	2
		Spherical filler	F1	15	15	15	15	15	15
			F2						
20			F3						
			F4						
			F5						
		Organic solvent G		400	400	400	400	400	400
25	Properties	Average grain size μm	2	2	2	8	2	2	
	Features of film coat	Surface roughness Rz μm	4	4	4	15	4	4	
		Number of convex portions 1,000 pcs/mm ²	250	250	250	10	250	250	
30	Number of sheets tested		5k	30k	15k	5k	15k	30k	

Table 6

			CE7	CE8	CE9	CE10	CE11	CE12	CE13
35	Paint configuration	Fluorine rubber	A1						
			A2	100	100	100	100	100	100
			A3						
			A4						
40		Reinforcing agent B		35	30	30	30	30	30
		Antacid C		15	15	15	15	15	15
		Vulcanizing agent D		0.2	7	2	2		2
45		Vulcanization accelerator E		2	2	0.2	7	2	2
		Spherical filler	F1	15	15	15	15		
			F2				15		
50			F3						
			F4					15	
			F5						15
		Organic solvent F		400	400	400	400	400	400
55	Properties	Average grain size μm		2	2	2	2	2	2

Table 6 (continued)

		CE7	CE8	CE9	CE10	CE11	CE12	CE13
Features of film coat	Surface roughness Rz μm	4	4	4	4	4	4	4
	Number of convex portions 1,000 pcs/mm ²	250	250	250	250	2000	2	100
Number of sheets tested		5k	40k	10k	45k	10k	5k	2k

[0171] As shown above, for the fixing devices in the examples 1 through 16, no generation of offset was observed in fixing tests on 60,000 sheets. Further, the fixing devices in the examples 1 through 16 are more excellent in durability of the fixing rollers as compared with the fixing devices in the comparative examples 1 through 13.

[0172] As described above, by using the fixing member, fixing device, and fixing method of the present invention, generation of offset can be reliably prevented for a long period of time. Further, the durability of the fixing roller will be improved. That is, when a toner is fixed, the adhesion of the toner to the surface of the fixing member is lowered, and the amount of the toner adhering to the surface layer material of the fixing member is reduced. As a result, generation of offset can be prevented. In addition, a fixing device having excellent durability can be obtained.

Claims

1. A fluorine rubber composition, used for a surface layer material of a fixing member to fix a toner transferred onto a recording material, comprising:

- (a) fluorine rubber having a polymerization degree based on vinylidene fluoride; and
- (b) at least one selected from the group consisting of a reinforcing agent, an antacid, a vulcanizing agent, a vulcanization accelerator, a spherical filler, and an organic solvent.

2. The fluorine rubber composition of claim 1, wherein said (b) contains said reinforcing agent, antacid, vulcanizing agent, vulcanization accelerator, a spherical filler, and organic solvent.

3. The fluorine rubber composition of claim 1, wherein said fluorine rubber contains at least one copolymer selected from the group consisting of: a copolymer of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene; a copolymer of tetrafluoroethylene, vinylidene fluoride and propylene; and a copolymer of vinylidene fluoride and hexafluoropropylene.

4. The fluorine rubber composition of claim 2, wherein said copolymer contains fluorine in a range from 60 wt% to 70 wt%.

5. The fluorine rubber composition of claim 1, wherein said (b) contains said reinforcing agent, and said reinforcing agent contains medium thermal carbon.

6. The fluorine rubber composition of claim 5, wherein said reinforcing agent is less than 5 μm in average grain size in a state of being dispersed in said surface layer material.

7. The fluorine rubber composition of claim 1, wherein said (b) contains said reinforcing agent, and said reinforcing agent is contained in a range from 20 parts to 40 parts by weight as against 100 parts by weight of said fluorine rubber.

8. The fluorine rubber composition of claim 1, wherein

said (b) contains said antacid, and
said antacid contains at least one of divalent metal oxide and hydroxide.

5 9. The fluorine rubber composition of claim 8, wherein
said antacid is less than 5 μm in average grain size in a state of being dispersed in said surface layer material.

10 10. The fluorine rubber composition of claim 9, wherein
said antacid is contained in a range from 5 parts to 20 parts by weight as against 100 parts by weight of said
fluorine rubber.

10 11. The fluorine rubber composition of claim 1, wherein

said (b) contains said vulcanizing agent, and
said vulcanizing agent contains at least one of polyol type compound and amine type compound.

15 12. The fluorine rubber composition of claim 1, wherein

said (b) contains said vulcanizing agent, and
said vulcanizing agent is contained in a range from 0.5 part to 5 parts by weight as against 100 parts by weight
20 of said fluorine rubber.

13. The fluorine rubber composition of claim 1, wherein

said (b) contains said vulcanization accelerator, and
said vulcanization accelerator contains at least one of organic quaternary phosphonium salt and organic qua-
25 ternary ammonium salt.

14. The fluorine rubber composition of claim 1, wherein

said (b) contains said vulcanization accelerator, and
said vulcanization accelerator is contained in a range from 0.5 part to 5 parts by weight as against 100 parts
30 by weight of said fluorine rubber.

15. The fluorine rubber composition of claim 1, wherein

said (b) contains said spherical filler, and
said spherical filler is over 80% in sphericity.

16. The fluorine rubber composition of claim 15, wherein
40 said spherical filler ranges from 0.5 μm to 10 μm in average grain size.

17. The fluorine rubber composition of claim 1, wherein

said (b) contains said spherical filler, and
said spherical filler is contained in a range from 5 parts to 30 parts by weight as against 100 parts by weight
45 of said fluorine rubber.

18. The fluorine rubber composition of claim 1, wherein

said (b) contains said organic solvent, and
said fluorine rubber is dissolved in said organic solvent.

19. The fluorine rubber composition of claim 2, wherein
55 said reinforcing agent and said spherical filler are uniformly dispersed.

20. A fixing member to fix a toner transferred onto a recording material, comprising:

a base material, and

a surface layer material disposed on a surface of said base material,
wherein said surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride.

5. 21. The fixing member of claim 20, wherein
said surface layer further contains at least one selected from the group consisting of a reinforcing agent, antacid, vulcanizing agent, vulcanization accelerator, and spherical filler.
- 10 22. The fixing member of claim 20, wherein
said fluorine rubber contains at least one copolymer selected from the group consisting of:
a copolymer of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene; a copolymer of tetrafluoroethylene, vinylidene fluoride and propylene; and a copolymer of vinylidene fluoride and hexafluoropropylene.
- 15 23. The fixing member of claim 22, wherein
said copolymer contains fluorine in a range from 60 wt% to 70 wt%.
- 20 24. The fixing member of claim 20, wherein
said surface layer material has numerous fine convex portions.
- 25 25. The fixing member of claim 24, wherein
each convex portion of the numerous fine convex portions has a spherical tip.
26. The fixing member of claim 24, wherein
the numerous fine convex portions are formed in a range from 5,000 pieces to one million pieces per square
25 millimeter.
27. The fixing member of claim 20, wherein
said surface layer material is less than 5 μm in surface roughness (Rz).
- 30 28. The fixing member of claim 20, wherein
said surface layer material further contains a spherical filler.
29. The fixing member of claim 28, wherein
said spherical filler is over 80% in sphericity.
- 35 30. The fixing member of claim 28, wherein
said spherical filler ranges from 0.5 μm to 10 μm in average grain size.
- 40 31. The fixing member of claim 28, wherein
said spherical filler is contained in a range from 5 parts to 30 parts by weight as against 100 parts by weight
of said fluorine rubber.
- 45 32. The fixing member of claim 20, wherein
said surface layer material further contains a spherical filler;
said surface layer material has a plurality of fine convex portions on its surface; and
each convex portion of the plurality of fine convex portions has a spherical tip that is formed depending upon
the shape of said spherical filler.
- 50 33. The fixing member of claim 20, wherein
said surface layer further contains a reinforcing agent;
said reinforcing agent contains medium thermal carbon; and
said reinforcing agent is less than 5 μm in average grain size in a state of being dispersed in said fluorine
55 rubber composition.
34. The fixing member of claim 20, wherein

said surface layer material further contains a reinforcing agent, antacid, and spherical filler;
said reinforcing agent is less than 5 μm in average grain size in a state of being dispersed in said surface layer material, and said reinforcing agent is contained in a range from 20 parts to 40 parts by weight as against 100 parts by weight of said fluorine rubber;

5 said antacid is less than 5 μm in average grain size in a state of being dispersed in said surface layer material, and said antacid is contained in a range from 5 parts to 20 parts by weight as against 100 parts by weight of said fluorine rubber; and

10 said spherical filler ranges from 0.5 μm to 10 μm in average grain size in a state of being dispersed in said surface layer material, and said spherical filler is contained in a range from 5 parts to 30 parts by weight as against 100 parts by weight of said fluorine rubber.

35. The fixing member of claim 20, wherein

said base material has a roller shape;

15 said base material includes a core bar, and a rubber elastic body disposed on the surface of said core bar; and said fluorine rubber composition has a circular section and is disposed on the surface of said rubber elastic body having a roller shape.

36. A fixing device to fix a toner transferred onto the surface of a recording material, comprising:

20 a fixing roller;

a press roller disposed opposing to said fixing roller; and

a web to apply a lubricant to the surface of said fixing roller,

25 wherein said fixing roller comprises a base material and a surface layer material disposed on the surface of said base material;

said surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride; and

30 a recording material having said toner transferred thereon passes between said fixing roller and said press roller while being pressed by said fixing roller and said press roller so that said surface layer material comes into contact with said toner, and then said toner is fixed on said recording material.

37. The fixing device of claim 36, wherein

said fluorine rubber contains at least one copolymer selected from the group consisting of:

35 a copolymer of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene; a copolymer of tetrafluoroethylene, vinylidene fluoride and propylene; and a copolymer of vinylidene fluoride and hexafluoropropylene.

38. The fixing device of claim 37, wherein

said copolymer contains fluorine in a range from 60 wt% to 70 wt%.

39. The fixing device of claim 36, wherein

40 said surface layer material further contains at least one selected from the group consisting of a reinforcing agent, antacid, vulcanizing agent, vulcanization accelerator, and spherical filler.

40. The fixing device of claim 36, wherein

45 said surface layer material has numerous fine convex portions.

41. The fixing device of claim 40, wherein

each convex portion of the numerous fine convex portions has a spherical tip.

42. The fixing device of claim 40, wherein

50 the numerous fine convex portions are formed in a range from 5,000 pieces to one million pieces per square millimeter.

43. The fixing device of claim 36, wherein

55 said surface layer material is less than 5 μm in surface roughness (Rz).

44. The fixing device of claim 36, wherein

said surface layer material further contains a spherical filler;
 said spherical filler is over 80% in sphericity; and
 said spherical filler ranges from 0.5 μm to 10 μm in average grain size.

45. The fixing device of claim 44, wherein

said spherical filler is contained in a range from 5 parts to 30 parts by weight as against 100 parts by weight of said fluorine rubber.

46. The fixing device of claim 36, wherein

said surface layer material further contains a reinforcing agent, antacid, and spherical filler;
 said reinforcing agent is less than 5 μm in average grain size in a state of being dispersed in said surface layer material, and said reinforcing agent is contained in a range from 20 parts to 40 parts by weight as against 100 parts by weight of said fluorine rubber;
 said antacid is less than 5 μm in average grain size in a state of being dispersed in said surface layer material, and said antacid is contained in a range from 5 parts to 20 parts by weight as against 100 parts by weight of said fluorine rubber; and
 said spherical filler ranges from 0.5 μm to 10 μm in average grain size in a state of being dispersed in said surface layer material, and said spherical filler is contained in a range from 5 parts to 30 parts by weight as against 100 parts by weight of said fluorine rubber.

47. The fixing device of claim 36, wherein

said base material includes a core bar, and a rubber elastic body disposed on said core bar; and
 said fixing roller further includes a heater disposed in said core bar.

48. A fixing method, comprising the steps of:

(a) transferring a toner onto a surface of a recording material;
 (b) passing said recording material, having said toner transferred thereon, between a rotating fixing roller and press roller, under pressures applied by said fixing roller and said press roller,
 wherein said fixing roller comprises a base material and a surface layer material disposed on the surface of said base material;
 said recording material passes between the rollers in a manner such that said toner is positioned at the fixing roller side;
 said surface layer contains fluorine rubber having a polymerization degree based on vinylidene fluoride; and
 (c) fixing said toner, pressed by said fixing roller and said press roller, on the surface of said recording material.

49. The fixing method of claim 48, wherein

said fluorine rubber contains at least one copolymer selected from the group consisting of:
 a copolymer of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene; a copolymer of tetrafluoroethylene, vinylidene fluoride and propylene; and a copolymer of vinylidene fluoride and hexafluoropropylene.

50. The fixing method of claim 49, wherein

said copolymer contains fluorine in a range from 60 wt% to 70 wt%.

51. The fixing method of claim 48, wherein

said surface layer material further contains at least one selected from the group consisting of a reinforcing agent, antacid, vulcanizing agent, vulcanization accelerator, and spherical filler.

52. The fixing method of claim 48, wherein

said surface layer material has numerous fine convex portions; and said surface layer material is greater in surface roughness than said recording material.

53. The fixing method of claim 52, wherein

each convex portion of the numerous fine convex portions has a spherical tip.

54. The fixing method of claim 52, wherein
the numerous fine convex portions are formed in a range from 5,000 pieces to one million pieces per square millimeter.

55. The fixing method of claim 48, wherein
said surface layer material is less than 5 μm in surface roughness (Rz).

56. The fixing method of claim 48, wherein

said surface layer material further contains a spherical filler;
said spherical filler is over 80% in sphericity; and
said spherical filler ranges from 0.5 μm to 10 μm in average grain size.

57. The fixing method of claim 56, wherein

said spherical filler is contained in a range from 5 parts to 30 parts by weight as against 100 parts by weight of said fluorine rubber.

58. The fixing method of claim 48, wherein

said surface layer material further contains a reinforcing agent, antacid, and spherical filler;
said reinforcing agent is less than 5 μm in average grain size in a state of being dispersed in said surface layer material, and said reinforcing agent is contained in a range from 20 parts to 40 parts by weight as against 100 parts by weight of said fluorine rubber;
said antacid is less than 5 μm in average grain size in a state of being dispersed in said surface layer material, and said antacid is contained in a range from 5 parts to 20 parts by weight as against 100 parts by weight of said fluorine rubber; and
said spherical filler ranges from 0.5 μm to 10 μm in average grain size in a state of being dispersed in said surface layer material, and said spherical filler is contained in a range from 5 parts to 48 parts by weight as against 100 parts by weight of said fluorine rubber.

59. A method of manufacturing a fixing device to fix a toner transferred onto a surface of a recording material, comprising the steps of:

- (a) manufacturing a fixing roller; and
- (b) manufacturing a press roller,

wherein the step of manufacturing said fixing roller comprises the steps of:

- (1) manufacturing a paint;
wherein the step of manufacturing said paint includes a step of mixing and dispersing fluorine rubber having a polymerization degree based on vinylidene fluoride, a vulcanizing agent, and a solvent;
- (2) applying said paint onto a surface of a base material having a spherical shape; and
- (3) drying and hardening said paint applied to the surface of the base material to form a surface layer material.

60. The method of manufacturing a fixing device of claim 59, wherein

said fluorine rubber contains at least one copolymer selected from the group consisting of:
a copolymer of tetrafluoroethylene, vinylidene fluoride and hexafluoropropylene; a copolymer of tetrafluoroethylene, vinylidene fluoride and propylene; and a copolymer of vinylidene fluoride and hexafluoropropylene.

61. The method of manufacturing a fixing device of claim 60, wherein

said copolymer contains fluorine in a range from 60 wt% to 70 wt%.

62. The method of manufacturing a fixing device of claim 59, wherein

said paint further contains at least one selected from the group consisting of a reinforcing agent, antacid, vulcanization accelerator, and spherical filler.

63. The method of manufacturing a fixing device of claim 59, wherein

said paint further contains a spherical filler;
 said spherical filler is over 80% in sphericity; and
 said spherical filler ranges from 0.5 μm to 10 μm in average grain size.

64. The method of manufacturing a fixing device of claim 63, wherein
 said spherical filler is contained in a range from 5 parts to 30 parts by weight as against 100 parts by weight
 of said fluorine rubber.

65. The method of manufacturing a fixing device of claim 59, wherein
 said vulcanizing agent contains at least one of a compound having polyol groups and a compound having
 amine groups, and
 said fluorine rubber reacts with said vulcanizing agent, and hardens.

66. The method of manufacturing a fixing device of claim 65, wherein
 said paint further contains a vulcanization accelerator;
 said vulcanization accelerator contains at least one of organic quaternary phosphonium salt and organic qua-
 ternary ammonium salt; and
 said fluorine rubber reacts with said vulcanizing agent and said vulcanization accelerator, and hardens.

67. The method of manufacturing a fixing device of claim 59, wherein
 said paint further contains a reinforcing agent, antacid, and spherical filler;
 said reinforcing agent is less than 5 μm in average grain size in a state of being dispersed in said surface layer
 material, and said reinforcing agent is contained in a range from 20 parts to 40 parts by weight as against 100
 parts by weight of said fluorine rubber;
 said antacid is less than 5 μm in average grain size in a state of being dispersed in said surface layer material,
 and said antacid is contained in a range from 5 parts to 20 parts by weight as against 100 parts by weight of
 said fluorine rubber; and
 said spherical filler ranges from 0.5 μm to 10 μm in average grain size in a state of being dispersed in said
 surface layer material, and said spherical filler is contained in a range from 5 parts to 48 parts by weight as
 against 100 parts by weight of said fluorine rubber.

68. The method of manufacturing a fixing device of claim 59, wherein
 said surface layer material has numerous fine convex portions; and
 said surface layer material is greater in surface roughness than said recording material.

69. The method of manufacturing a fixing device of claim 59, wherein
 each convex portion of the numerous fine convex portions has a spherical tip.

70. The method of manufacturing a fixing device of claim 59, wherein
 the numerous fine convex portions are formed in a range from 5,000 pieces to one million pieces per square
 millimeter.

71. The method of manufacturing a fixing device of claim 59, wherein
 said surface layer material is less than 5 μm in surface roughness (Rz).

Fig. 1




Fig. 2




Fig. 3

PRIOR ART




Fig. 4

PRIOR ART




Fig. 5

PRIOR ART





Fig. 6

PRIOR ART



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 160 284 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
21.01.2004 Bulletin 2004/04

(51) Int Cl.7: **C08L 27/12, B32B 27/30,
C09D 127/16, G03G 15/20**

(43) Date of publication A2:
05.12.2001 Bulletin 2001/49

(21) Application number: **01112037.5**

(22) Date of filing: **23.05.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **01.06.2000 JP 2000164293**

(71) Applicant: **MATSUSHITA ELECTRIC INDUSTRIAL
CO., LTD.**
Kadoma-shi, Osaka 571-8501 (JP)

(72) Inventors:
• **Kiyomura, Yoshihiro**
Oonjo-shi, Fukuoka 816-0941 (JP)
• **Kama, Hirofumi**
Oomuta-shi, Fukuoka 836-0006 (JP)
• **Noda, Hiroyuki**
Ogoori-shi, Fukuoka 838-0107 (JP)

(74) Representative: **Balsters, Robert et al**
Novagraaf SA
25, Avenue du Pailly
1220 Les Avanchets - Geneva (CH)

(54) **Fluorine rubber composition, fixing member, fixing device, fixing method, and method of manufacturing fixing device**

(57) A fluorine rubber composition used for the surface layer material of a fixing member to fix a toner transferred onto a recording material comprises fluorine rubber having a polymerization degree based on vinylidene fluoride. The fixing member includes a base material, and a surface layer material disposed on the surface of the base material, and the surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride. Preferably, the fluorine rubber composition contains a reinforcing agent, antacid,

vulcanizing agent, vulcanization accelerator, spherical filler, and solvent. Preferably, the fixing member has numerous fine convex portions on its surface. Accordingly, the amount of the toner adhering to the surface of the fixing member is reduced. Thus, generation of offset trouble can be reliably prevented for a long period of time. As a result, the durability of the fixing member will be improved.

EP 1 160 284 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 11 2037

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (InLCI.7)
X	EP 0 867 474 A (XEROX CORP) 30 September 1998 (1998-09-30) * page 3, line 50 - line 51 * * page 4, line 48 - page 5, line 10 * * page 6, line 23 - page 7, line 19; claims *	1-19	C08L27/12 B32B27/30 C09D127/16 G03G15/20
X	US 4 990 406 A (KAPPLER PATRICK ET AL) 5 February 1991 (1991-02-05) * column 1, line 49 - line 51 * * column 3, line 17 - line 26 * * column 3, line 54 - line 67 *	1	
A	* claims *	2-19	
X	EP 0 515 221 A (NIPPON ZEON CO) 25 November 1992 (1992-11-25)	1	
A	* page 2, line 14 - line 52 *	2-19	
A	US 5 177 550 A (UEHARA YASUHIRO ET AL) 5 January 1993 (1993-01-05) * column 2, line 28 - line 40; claims 1,3; figure 6 *	20-71	
A	US 4 640 600 A (HIRABAYASHI HIROMITSU ET AL) 3 February 1987 (1987-02-03) * claims 11,15,16; figure 1 *	20-71	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (InLCI.7)
			C08L C09D G03G
Place of search MUNICH		Date of completion of the search 25 November 2003	Examiner Iraegui Retolaza, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P4/C01)



European Patent
Office

Application Number

EP 01 11 2037

CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

- ☐ Only part of the claims have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid, namely claim(s):
- ☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

see sheet B

- ☒ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.
- ☐ As all searchable claims could be searched without effort justifying an additional fee, the Search Division did not invite payment of any additional fee.
- ☐ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid, namely claims:
- ☐ None of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims, namely claims:



European Patent
Office

LACK OF UNITY OF INVENTION
SHEET B

Application Number

EP 01 11 2037

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

1. Claim : 1 to 19

A fluorine rubber composition comprising fluorine rubber having a polymerization degree based on vinylidene fluoride and at least one selected from the groups consisting of a reinforcing agent, an antacid, a vulcanizing agent, a vulcanization accelerator, a spherical filler and an organic solvent.

2. Claim : 20 to 35

A fixing member comprising a base material and a surface layer material, wherein said surface layer material contains fluorine rubber having a polymerization degree based on vinylidene fluoride.

3. Claim : 36 to 47

A fixing device comprising a fixing roller, a press roller and a web, wherein said fixing roller comprises a base material and a surface layer material containing fluorine rubber having a polymerization degree based on vinylidene fluoride.

4. Claim : 48 to 58

A fixing method comprising the steps of transferring a toner onto a surface of a recording material, passing said recording material between a rotating fixing roller, wherein said fixing roller comprises a base material and a surface layer material containing fluorine rubber having a polymerization degree based on vinylidene fluoride, and fixing said toner on the surface of said recording material.

5. Claim : 59 to 71

A method of manufacturing a fixing device to fix a toner transferred onto a surface of a recording material comprising the steps of manufacturing a fixing roller and manufacturing a press roller, wherein the step of manufacturing said fixing roller comprises the steps of manufacturing a paint which includes the step of mixing and dispersing fluorine rubber having a polymerization degree based on vinylidene fluoride, a vulcanizing agent and a solvent, applying said paint onto a surface of a base material and drying and hardening said paint.

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 01 11 2037

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-11-2003

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0867474	A	30-09-1998	US	5945223 A	31-08-1999
			BR	9800950 A	23-11-1999
			CA	2227075 A1	24-09-1998
			DE	69817242 D1	25-09-2003
			EP	0867474 A1	30-09-1998
			JP	10310738 A	24-11-1998
US 4990406	A	05-02-1991	FR	2636959 A1	30-03-1990
			AT	90717 T	15-07-1993
			AU	619347 B2	23-01-1992
			AU	4230689 A	05-04-1990
			CA	1325302 C	14-12-1993
			DE	68907173 D1	22-07-1993
			DE	68907173 T2	11-11-1993
			DK	478689 A	30-03-1990
			EP	0364316 A1	18-04-1990
			ES	2041021 T3	01-11-1993
			FI	894607 A ,B,	30-03-1990
			IE	63087 B1	22-03-1995
			JP	1672929 C	12-06-1992
			JP	2123152 A	10-05-1990
			JP	3036857 B	03-06-1991
			KR	9605435 B1	25-04-1996
			NO	893864 A ,B,	30-03-1990
			PT	91841 A ,B	30-03-1990
EP 0515221	A	25-11-1992	JP	6315982 A	15-11-1994
			DE	69226900 D1	15-10-1998
			DE	69226900 T2	24-06-1999
			EP	0515221 A2	25-11-1992
US 5177550	A	05-01-1993	JP	2586239 B2	26-02-1997
			JP	4251277 A	07-09-1992
			KR	9408793 B1	26-09-1994
US 4640600	A	03-02-1987	JP	2052637 C	10-05-1996
			JP	5054112 B	11-08-1993
			JP	59126576 A	21-07-1984
			JP	60014270 A	24-01-1985
			JP	60017472 A	29-01-1985
			JP	1696923 C	28-09-1992
			JP	3061948 B	24-09-1991
			JP	59071074 A	21-04-1984
			JP	1711438 C	11-11-1992
			JP	3076461 B	05-12-1991
			JP	59074579 A	27-04-1984

EPO FORM P/038

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82